

## **DATASHEET**

**Quality; SPEYPACK® SILVER** 

Origin; Europe

SPEYPACK ECO SILVER		DATA	TOLERANCE
Grammage	g/m²	650	±5%
Caliper	μm	770	±7.5%
Moisture	%	8.0	±0.5%
Smoothness µm (top)	ISO8791-4	•	<2.0 µm
Stiffness CD	(50mm/5° - DIN53121)	880	-15%
Stiffness MD	(50mm/5° - DIN53121)	440	-15%
ISO brightness +UV	ISO2470	95%	±3%

Tolerances, when specified, are based on 95% confidence limits on single mill measurements of random samples measured in manufacturing conditions. Indicative technical values (23°C RH 50%).

Issued 01.04.2017.

